

412240

Fecha de Alta

10-09-2015

Versión

7 - 27/04/2017

RESTORA SELLADORA AL AGUA BLANCA



FAMILY TRATAMIENTOS DE LA MADERA

LINE PROTECTORES AL AGUA (P. A.)

DESCRIPTION AND NATURE

Acrylic-urethane primer. Excellent brochability, does not smell. Great adhesion and excellent whiteness and coverage. Great filling power with easy sanding.

USAGES

Outdoors/Indoors

Cement

Plaster

Plaster

Wood

PROPERTIES

Penetration power
 No sanding necessary for repainting. Non expensive manteinance
 Good adhesion
 Penetration power
 Good applicability
 Drying fast
 Odourless when dry
 Good adhesion

TECHNICAL CHARACTERISTICS

Referencia Color	RESTORA SELLADORA AL AGUA BLANCA
Finish	Satin
Specific weight	1,43± 0,05 kg/l
Viscosity	40 +/- 5 PO
Solids in volume	35± 1
Solids in weight	56± 1
VOC	Cat. d/BA 150/130 (2007/2010): 49,11 g/l
Aproximated performance by coat	7-10 m ² /L

Dry to touch	(20°C HR 60%): 1 - 2 h.Sanding: 12-24h according to performance
Dry to repaint	(20°C HR 60%):Min 24h
Colours	white

SURFACE PREPAIRING

New surfaces

Cement mortar, plaster and by products.

- Wait till complete drying of product (30 days minimum).
- Surface should be totally dry.
- Remove off any efflorescences and neutralize alkaline surfaces.
- Remove off any foreing products or remains.
- Cover surface imperfections with suitable plaster or putty.
- Mildewed surfaces should be treated with fungicide.

New wood:

- Only apply on wood with less than 12% moisture content.
- Sandpaper and eliminate any remains in joints and mechanical faults.

RESTORA SELLADORA AL AGUA BLANCA

-Old wood should be previously sandpapered and primed. Remove any dust by brushing it off or using any other mechanical system.

-Cover surface imperfections with plaster or putty.

Restoring and maintenance

-Paints in bad condition should be removed by mechanical systems or chemical products proceeding then as per new surfaces.

-Painted or varnished, Remove off foreign remains, or areas in bad condition, sandpaper slightly, brush any resulting dust and proceed as per new wood.

-If the have been varnished, apply a stripping product or use a mechanical system and proceed as per new wood. If surfaces are in good condition, sandpaper slightly, brush any resulting dust and proceed as per new wood. Allows to be painted over.

Painted construction materials: (plaster, cement and by-products):

-Remove off any foreign remains or areas in bad condition, sandpaper slightly, brush any resulting dust and proceed as per new surfaces.

WAY OF USE

Application Notes

-Stir product thoroughly.

-Follow application guidelines shown on table below.

-Do not apply product at high temperatures or overheated surfaces exposed to sunshine.

-Keep room well ventilated while product is drying.

-Do not apply when moisture contents is over 80%.

Solvent for dilution and cleaning

Way of use	Aproximate dilution
Painting brush	0-10%
Roller	0-10%
Air-less gun	10-30%
Air-mix gun	10-30%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
New work			
MAX	Restora Selladora al agua	Restora Selladora al agua	Restora Esmalte Acrilico; Barnices o Lasures al Agua.
STD	Restora Selladora al agua		Restora Esmalte Acrilico; Barnices o Lasures al Agua.
New wood indoor/outdoor			
MAX	Restora Selladora al agua	Restora Selladora al agua	Restora Esmalte Acrilico; Barnices o Lasures al Agua.
STD	Restora Selladora al agua		Restora Esmalte Acrilico; Barnices o Lasures al Agua.

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

RESTORA SELLADORA AL AGUA BLANCA

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.375 L, 0.75 L